

# Ecoflex potable HDPE coils

## Project information

Job name:	Location:
Engineer:	Date submitted:
Contractor:	Submitted by:
Manufacturer's representative:	Approved by:

## Technical data

Material	PEX
Temp/pressure ratings	73 °F (23 °C) at 160 psi (11 bar) 180 °F (82 °C) at 100 psi (6.9 bar) 200 °F (93 °C) at 80 psi (5.5 bar)

## Product information and application use

Uponor's ASTM Ecoflex® Potable HDPE features high-density polyethylene (HDPE) service pipe protected by multilayer PEX-foam insulation and covered by a corrugated, waterproof HDPE jacket. Use Ecoflex Potable HDPE for cold potable-water, cooling and low-temperature heating applications.



Part name	Part no.	Inner diameter pipe [Inch]	Outer diameter pipe [Inch]	Weight per UOM [lbs/UOM]
3" Potable HDPE with 6.9" Jacket, 300-ft. coil	5116930	2.398	3.125	2.4
4" Potable HDPE with 7.9" Jacket, 300-ft. coil	5117940	3.169	4.125	3.6

## Installation

Install Ecoflex Potable HDPE in cold potable-water, chilled-water, cooling and low-temperature heating applications. Join pipes through fusion welding, electro-fusion fittings or HDPE compression fittings (not sold by Uponor). For additional information, refer to the Uponor Pre-insulated Pipe Systems Design and Installation Manual.

## Related applications

- Pre-Insulated Pipe Systems
- Radiant Heating and Cooling Systems
- Permafrost Prevention Systems
- Turf Conditioning Systems

## Notes

Operating Limits: -30°F to 73°F at 160 psig (-34°C to 23°C at 11.0 bar) -30°F to 100°F at 125 psig (-34°C to 38°C at 8.6 bar) -30°F to 120°F at 101 psig (-34°C to 49°C at 6.9 bar) -30°F to 140°F at 80

## Footnotes

-

## Contact information

Uponor Inc.  
5925 148th Street West  
Apple Valley, MN 55124  
T 800.321.4739  
F 952.891.2008

Uponor Ltd.  
6510 Kennedy Road  
Mississauga, ON L5T 2X4  
T 888.594.7726  
F 800.638.9517