

Ecoflex potable HDPE coils

Project information

Job name:	Location:
Engineer:	Date submitted:
Contractor:	Submitted by:
Manufacturer's representative:	Approved by:

Technical data

Material	PEX
Temp/pressure ratings	73 °F (23 °C) at 160 psi (11 bar)
	180 °F (82 °C) at 100 psi (6.9 bar)
	200 °F (93 °C) at 80 psi (5.5 bar)

Product information and application use

Uponor's ASTM Ecoflex® Potable HDPE features high-density polyethylene (HDPE) service pipe protected by multilayer PEX-foam insulation and covered by a corrugated, waterproof HDPE jacket. Use Ecoflex Potable HDPE for cold potable-water, cooling and low-temperature heating applications.



Part name	Part no.	Inner diameter pipe [inch]	Outer diameter pipe [inch]	Weight per UOM [lbs/UOM]
3" Potable HDPE with 6.9" Jacket, 300-ft. coil	5116930	2.398	3.125	2.4
4" Potable HDPE with 7.9" Jacket, 300-ft. coil	5117940	3.169	4.125	3.6

Installation	Related applications
Install Ecoflex Potable HDPE in cold potable-water, chilled-water, cooling and low-temperature heating applications. Join pipes through fusion welding, electro-fusion fittings or HDPE compression fittings (not sold by Uponor). For additional information, refer to the Uponor Pre-insulated Pipe Systems Design and Installation Manual.	Pre-Insulated Pipe Systems
	Radiant Heating and Cooling Systems
	Permafrost Prevention Systems
	Turf Conditioning Systems

Notes
Operating Limits: -30°F to 73°F at 160 psig (-34°C to 23°C at 11.0 bar) -30°F to 100°F at 125 psig (-34°C to 38°C at 8.6 bar) -30°F to 120°F at 101 psig (-34°C to 49°C at 6.9 bar) -30°F to 140°F at 80

Footnotes	Contact information
-	<div>Uponor Inc. 5925 148th Street West Apple Valley, MN 55124 T 800.321.4739 F 952.891.2008</div> <div>Uponor Ltd. 6510 Kennedy Road Mississauga, ON L5T 2X4 T 888.594.7726 F 800.638.9517</div>