


GF Malleable Fittings plug plain 291 2 1/2 B

1154141

- Plug, plain, ISO/EN TB
- 'ST' these types of fittings are made from steel (galvanised finish = electroplated)
- Not suitable for drinking water installations
- Steel parts are made solid.



About GF Malleable Fittings plug plain 291

Specification


- Unique Whiteheart ductile Cast Iron to EN-GJMW-400-5 to BS EN 1562, design symbol A
- Thread type BSP - R or Rp to BS EN 10226-1 / ISO 7-1
- Union or flat-nut thread types to BS EN 228-1
- Manufactured to BS EN 10242 (ISO 49)
- Cast Iron is fire class A1 to BS EN 13501-1 (CWFT) acc. to Commission Decision 96/603/EC (as amended)
- Natural Black or Galvanized (99.995 zinc)
- Coated with medical-grade oil for corrosion protection
- Suitable for systems covered by the Pressure Equipment Safety Regulation:2016
- Max. pressure 25 bar up to 120 degrees, between 120-300 degrees use interpolated values, Max. 20bar at 300 degrees
- Sizes from 1/4" to 4"

Application

- Heating - LTHW, MTHW and HTHW
- Steam
- Chilled water and cooling applications
- Compressed air
- Fuel gases
- Fuel oils
- Fire defence / sprinklers

GF Malleable Fittings plug plain 291 2 1/2 B

1154141



Product code

Item no EAN	7611205330217
Item no GF	770291110
Item no GTIN	07611205330217
Item no RSK	1320092
Item no VVS	004291113

Dimensions

Item Unit Height	76
Item Unit Length	76
Item Unit Weight	0,462
Item Unit Width	52
Item_UOM	pce

Packaging

Packaging GTIN PL1	07611205130213
Packaging GTIN PL4	06414900120920
Packaging Height PL1	200
Packaging Height PL4	729
Packaging Length PL1	260
Packaging Length PL4	1200
Packaging Quantity PL1	25
Packaging Quantity PL4	1350
Packaging Type PL1	Base_Box
Packaging Type PL4	Pallet
Packaging Volume PL1	0,00988
Packaging Volume PL4	0,69984
Packaging Weight PL1	11,764
Packaging Weight PL4	643,7
Packaging Width PL1	190

Packaging Width PL4

800

Technical documents

Download documents here 

Uponor UK

Blackmor Lane The Pavilion
WD18 8GA, Watford
UK

T +44 (0)1923 927000
E enquiries.uk@uponor.com

www.uponor.com/en-gb