

Wirsbo hePEX coils

Project information	
Job name:	Location:
Engineer:	Date submitted:
Contractor:	Submitted by:
Manufacturer's representative:	Approved by:

Technical data

Temp/pressure ratings

Material PEX

73 °F (23 °C) at 160 psi (11 bar) 180 °F (82 °C) at 100 psi (6.9 bar)

200 °F (93 °C) at 80 psi (5.5 bar)

Product information and application use

Wirsbo hePEX™ tubing is used for closed-loop heating and cooling applications, including radiant and hydronic distribution. It has an EVOH oxygen diffusion barrier that meets German DIN 4726/9.

Note: Temperature and pressure ratings stated are hydrostatic ratings. For domestic hot-water (DHW) and DHW recirculation installations, operating conditions should not exceed 140°F (60°C) at 80 psi (5.5 bar) in accordance with ASTM F2023. For additional information regarding application-specific temperature and pressure ratings, refer to the Uponor PEX Piping Systems Design and Installation Manual.



Part name	Part no.	Codes	Standards	Listings
Wirsbo hePEX coils	All	IMC UPC IBC IRC NBC of Canada IPC UFGS NPC of Canada UMC NSPC	ASTM F1960 ASTM E119/UL 263 ASTM F876 ASTM E84 ASTM F2023 ASTM E814/ULC S115 ASTM F877 CSA B137.5 ULC S102.2 CSA B214 NSF/ANSI/CAN 61 ULC S101 NSF/ANSI 14	IAPMO-ES ICC-ES-PMG cNSFus- rfh cNSFus-pw CCMC PPI TR- 4 CSA UL U.P.Code cQAlus P321

Installation		Related applications
	Radiant Heating and Cooling Systems	
		Permafrost Protection Systems
Approved fitting system is ProPEX®. 1 Refer to the Uponor Com (CDAM) or Hydronic Piping Design Assistance Manual (HPDAM)	•	Turf Conditioning Systems Chilled water distribution
(OD) Will of Trydronio Tiping Design Assistance Mandai (Til D) Wil	Tor future information.	
		Hot water distribution

Footnotes	Contact in	Contact information	
	Uponor Inc.	Uponor Ltd.	
	5925 148th Street West	6510 Kennedy Road	
•	Apple Valley, MN 55124	Mississauga, ON L5T 2X4	
	T 800.321.4739	T 888.594.7726	
	F 952.891.2008	F 800.638.9517	