

Uponor PP-RCT crossovers (molded)

Project information


Job name:	Location:
Engineer:	Date submitted:
Contractor:	Submitted by:
Manufacturer's representative:	Approved by:

Technical data

Material	PP-RCT
Temp/pressure ratings	73 °F (23 °C) at 340 psi (23.44 bar)
	140 °F (60 °C) at 190 psi (13.1 bar)
	180 °F (82 °C) at 100 psi (6.9 bar)

Product information and application use

Use Uponor PP-RCT crossovers with Uponor PP-RCT mechanical pipe to convey water for hydronic heating and cooling or industrial applications.



Part name	Part no.	End Type 1	End Type 2
Uponor PP-RCT Crossover, Molded, 1" x 1	PR4481010	Socket 1"	Socket 1"
Uponor PP-RCT Crossover, Molded, 1/2" x 1/2	PR4485050	Socket 1/2"	Socket 1/2"
Uponor PP-RCT Crossover, Molded, 3/4" x 3/4	PR4487575	Socket 3/4"	Socket 3/4"

Part name	Part no.	Codes	Standards	Listings
Uponor PP-RCT crossovers (molded)	All	CMC IMC UMC	ASTM E84 NSF-14 ASTM F2389 CSA B137.11	ICC-ES-PMG 1106 IAPMO-R&T 8358 QAI P321-5 IAPMO K-12775

Installation

Use approved butt-fusion connection methods. Refer to the Uponor PP-RCT manual for complete details.

Related applications

Hydronic heating and cooling systems  
Industrial

Footnotes

-

Contact information

Uponor Inc.  
5925 148th Street West  
Apple Valley, MN 55124  
T 800.321.4739  
F 952.891.2008

Uponor Ltd.  
6510 Kennedy Road  
Mississauga, ON L5T 2X4  
T 888.594.7726  
F 800.638.9517