

Bobinas de tuberías hePEX de Wirsbo

Project information	
Job name:	Location:
Engineer:	Fecha de envío:
Contractor:	Presentada por:
Manufacturer's representative:	Approved by:

Technical data

Material PEX

Temp/pressure ratings 73 °F (23 °C) at 160 psi (11 bar) 180 °F (82 °C) at 100 psi (6.9 bar) 200 °F (93 °C) at 80 psi (5.5 bar)

Prop 65 label required? No

Product information and application use

Wirsbo hePEX™ tubing is used for closed-loop heating and cooling applications, including radiant and hydronic distribution. It has an EVOH oxygen diffusion barrier that meets German DIN 4726/9.

Note: Temperature and pressure ratings stated are hydrostatic ratings. For domestic hot-water (DHW) and DHW recirculation installations, operating conditions should not exceed 140°F (60°C) at 80 psi (5.5 bar) in accordance with ASTM F2023. For additional information regarding application-specific temperature and pressure ratings, refer to the Uponor PEX Piping Systems Design and Installation Manual.



Part name	Part no.	Codes	Standards	Listings
			ASTM F1960 ASTM E119/UL	
		IMC UPC IBC IRC NBC of	263 ASTM F876 ASTM E84 ASTM	IAPMO-ES ICC-ES-PMG cNSFus-
Bobinas de tuberías hePEX de Wirsbo	All	Canada IPC UFGS NPC of	F2023 ASTM E814/ULC S115 ASTM	rfh cNSFus-pw CCMC PPI TR-
		Canada UMC NSPC	F877 CSA B137.5 ULC S102.2 CSA	4 CSA UL U.P.Code cQAlus P321
			B214 NSF-61 ULC S101 NSF-14	

Installation Related applications

Approved fitting system is ProPEX®. 1 Refer to the Uponor Complete Design Assistance Manual (CDAM) or Hydronic Piping Design Assistance Manual (HPDAM) for further information.

Radiant Heating and Cooling Systems

Permafrost Protection Systems

Turf Conditioning Systems

Chilled water distribution

Hot water distribution

Footnotes	Contact information		
	Uponor Inc.	Uponor Ltd.	
	5925 148th Street West	6510 Kennedy Road	
•	Apple Valley, MN 55124	Mississauga, ON L5T 2X4	
	T 800.321.4739	T 888.594.7726	
	F 952.891.2008	F 800.638.9517	