
Adaptateurs filetés mâles ProPEX en EP

Renseignements sur le projet

Nom du poste :	Lieu :
Ingénieur :	Date de soumission:
Entrepreneur :	Présentée par:
Représentant du fabricant :	Approuvé par :

Données techniques

Material	Engineered Polymer
Temp/pressure ratings	73 °F (23 °C) at 160 psi (11 bar) 180 °F (82 °C) at 100 psi (6.9 bar) 200 °F (93 °C) at 80 psi (5.5 bar)



Informations sur le produit et utilisation de l'application

The ProPEX® engineered polymer (EP) male threaded adapter combines durable polymer material with the reliable ASTM F1960 connection professionals have come to depend on for a solution that stands the test of time.

Note: Temperature and pressure ratings stated are hydrostatic ratings. For domestic hot-water (DHW) and DHW recirculation installations, operating conditions should not exceed 140°F (60°C) at 80 psi (5.5 bar) in accordance with ASTM F2023. For additional information regarding application-specific temperature and pressure ratings, refer to the Uponor PEX Piping Systems Design and Installation Manual.

	Nom de la pièce	Numéro de pièce	Cv	End Type 1	End Type 2
	ProPEX EP Male Threaded Adapter, 1/2" PEX x 1/2" NPT	Q4625050	5	ProPEX 1/2"	MNPT 1/2"
✔	ProPEX EP Male Threaded Adapter, 3/4" PEX x 3/4" NPT	Q4627575	11.3	ProPEX 3/4"	MNPT 3/4"
	ProPEX EP Male Threaded Adapter, 1" PEX x 1" NPT	Q4621010	19.9	ProPEX 1"	MNPT 1"

Nom de la pièce	Numéro de pièce	Les codes	Normes	Annonces
Adaptateurs filetés mâles ProPEX en EP	All	UPC|IRC|IPC|NPC of Canada	ASTM F1960|CSA B137.5|NSF-61|NSF-14|NSF-372|ASTM F877	U.P.Code|cNSFus-pw

L'installation

Use a minimum of three wraps of PTFE thread-seal tape. If using thread-sealant paste in addition to tape, consult the paste manufacturer for compatibility with polymer fittings. To avoid cross-threading, turn the fitting counterclockwise against the female threads until the threads drop into place. Then, tighten accordingly

Applications connexes

PEX-a Plumbing Systems

Plumbing Systems

Pre-Insulated Pipe Systems

Notes de bas de page

-

Coordonnées de la personne-ressource

Uponor Inc.
5925 148th Street West
Apple Valley, MN 55124
T 800.321.4739
F 952.891.2008

Uponor Ltd.
6510 Kennedy Road
Mississauga, ON L5T 2X4
T 888.594.7726
F 800.638.9517

© 2024 Uponor Amérique du Nord. Tous droits réservés