

Raccords WIPEX conformes à la norme ASTM

Renseignements sur le projet

Nom du poste :	Lieu :
Ingénieur :	Date de soumission:
Entrepreneur :	Présentée par:
Représentant du fabricant :	Approuvé par :

Données techniques

Material	Brass
Temp/pressure ratings	73 °F (23 °C) at 160 psi (11 bar) 180 °F (82 °C) at 100 psi (6.9 bar) 200 °F (93 °C) at 80 psi (5.5 bar)
Prop 65 label required?	Yes

Informations sur le produit et utilisation de l'application

WIPEX™ Fittings are used for all types of Uponor's crosslinked polyethylene (PEX-a) tubing applications. Dezincification-resistant (DZR) brass fittings are safe for direct burial in soil.



Nom de la pièce	Numéro de pièce	A [Inch]	B [Inch]	C [Inch]	Weight per UOM [lbs/UOM]	Equivalent length branch [ft]	End Type 1	End Type 2
WIPEX Fitting 1" PEX x 1" NPT	5550010	-	-	-	0.63	-	Compression 1"	MNPT 1"
WIPEX Fitting 2" PEX x 2" NPT	5550020	-	-	-	2.14	-	Compression 2"	MNPT 2"
WIPEX Fitting 2 1/2" x 2" NPT	5550025	-	-	-	2.74	-	Compression 2-1/2"	MNPT 2"
WIPEX Fitting 3" x 2 1/2" NPT	5550030	-	-	-	4.57	-	Compression 3"	MNPT 2-1/2"
WIPEX Fitting 4" x 4" NPT	5550040	5.52	5.551	4.724	10	-	Compression 4"	MNPT 4"

L'installation

Use DZR brass adapters to transition Uponor PEX tubing to male NPT thread. Use EPDM O-rings between the different parts for sealing. For more information, refer to the Uponor WIPEX Fittings Instruction Sheet.

Applications connexes

- Pre-Insulated Pipe Systems
- Radiant Heating and Cooling Systems
- Permafrost Prevention Systems
- Turf Conditioning Systems
- PEX-a Plumbing Systems
- AquaSAFE™ Fire Safety Systems

Les codes	Normes	Annonces
IMC JMC	CSA B137.5 NSF-14 ASTM F877	IAPMO-ES

Notes de bas de page

Coordonnées de la personne-ressource

Uponor Inc.
5925 148th Street West
Apple Valley, MN 55124
T 800.321.4739
F 952.891.2008

Uponor Ltd.
6510 Kennedy Road
Mississauga, ON L5T 2X4
T 888.594.7726
F 800.638.9517